



Date Prepared: December 15, 2015

SUPRENE® 501A

SUPRENE EPDM 501A is a low Mooney Viscosity and ENB type grade.

It shows excellent mill processability.

It has good flow and is suitable for molding complicated shaped products.

It is also suitable for extrusion of cable.

Main uses of SUPRENE EPDM 501A are found in gasket, roll, electric parts, various rubber coated fabrics and general industrial parts.

Raw Polymer Properties

	Test Method	Unit	Min.	Max.	Typical Value
Mooney Viscosity,	ASTM D1646	-	41	51	46
(ML 1+4, 100°C unmilled)					
Ethylene Content *	ASTM D3900	wt%	50	56	53
ENB Content	ASTM D6047	wt%	3.1	5.1	4.1
Oil Content	-	phr	-	-	-
Specific Gravity	ASTM D792	-	-	-	0.86
Volatile Matter	ASTM D5668	wt%	-	0.8	-
Ash	ASTM D5667	wt%	-	0.15	-
Physical Form,	-	-	-	-	25kg
(kg/bale)					(Dense Bale)

^{*} Ethylene Content + Propylene Content = 100%

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.

^{*} After production date, shelf life time is 3 years. And we recommend this product should be stored dry and at temperature < 30 °C. Exposure to light has to be avoided.