



Date Prepared: December 15, 2015

SUPRENE® 505A

SUPRENE EPDM 505A has lower Mooney viscosity than SUPRENE EPDM 505, and its mill processability is further improved.

It is Possible to mold with SUPRENE EPDM 505A various molded products within a short time because of its fast cure rate.

When SUPRENE EPDM 505A blended with diene type rubber, its dispersion is excellent. It can also be used more effectively by taking advantage of good ozone resistances.

SUPRENE EPDM 505A is suitable for sponge made by continuous curing. Low density sponge can be obtained through the curing.

It can also be used in various applications such as automotive tires, rubber coated fabrics, and automotive parts.

Raw Polymer Properties

| | Test Method | Unit | Min. | Max. | Typical Value |
|--------------------------|--------------------|------|------|------|---------------|
| Mooney Viscosity, | ASTM D1646 | - | 40 | 50 | 45 |
| (ML 1+4, 100°C unmilled) | | | | | |
| Ethylene Content * | ASTM D3900 | wt% | 52 | 58 | 55 |
| ENB Content | ASTM D6047 | wt% | 8.4 | 10.4 | 9.4 |
| Oil Content | - | phr | - | - | - |
| Specific Gravity | ASTM D792 | - | - | - | 0.86 |
| Volatile Matter | ASTM D5668 | wt% | - | 8.0 | - |
| Ash | ASTM D5667 | wt% | - | 0.15 | - |
| Physical Form, | - | - | - | - | 25kg |
| (kg/bale) | | | | | (Dense Bale) |

^{*} Ethylene Content + Propylene Content = 100%

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Corporation's invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.

^{*} After production date, shelf life time is 3 years. And we recommend this product should be stored dry and at temperature < 30 °C. Exposure to light has to be avoided.